

Selection & Specification Data

Generic Type	Epoxy Polyamide
Description	Versatile corrosion resistant coating. Used either as a primer, intermediate coat, or self-priming finish over steel and inorganic zinc primers. May be topcoated with itself, or a broad variety of high performance finish coats. Has surface tolerant properties.
Features	<ul style="list-style-type: none"> ▪ Ready to apply after mixing; no sweat-in time or thinning required. ▪ Economical fit for use epoxy ▪ Available in a variety of rapid tint colors ▪ Attractive low sheen for tank exteriors ▪ Used as a primer, an intermediate or finish coat ▪ Can be applied over power tool cleaned surfaces ▪ VOC compliant to current AIM regulations
Color	Primer color (0700) gray. Variety of other finish coat colors in rapid tint service. Use Bright White (F800) for tank exterior finish.
Finish	Low sheen
Primers	Self-priming. May be applied over organic and inorganic zinc rich primers. A mist coat may be required to minimize bubbling over zinc rich primers.
Topcoats	Acrylics, Alkyds, Epoxies, Polyurethanes
Dry Film Thickness	<p>3.0-5.0 mils (75-125 microns) per coat as a primer or an intermediate. Two coats at 3-5 mils (75-125 microns) per coat may be used direct-to-metal.</p> <p>4.0-6.0 mils (100-150 microns) per coat as a finish coat over a primer. Do not exceed 10 mils (250 microns) in a single coat. Excessive film thickness over inorganic zincs may increase damage during shipping or erection.</p>
Solids Content	By Volume: 60% ± 2%
Theoretical Coverage Rate	<p>962 mil ft² (24.0 m²/l at 25 microns)</p> <p>320 ft² at 3 mils (8.0 m²/l at 25 microns)</p> <p>Allow for loss in mixing and application</p>
VOC Values	<p>As supplied: 2.87 lbs./gal (345 g/l)</p> <p>Thinned:</p> <p>10 oz/gal w/ #10: 3.18 lbs./gal (382 g/l)</p> <p>15 oz/gal w/ #10: 3.32 lbs./gal (398 g/l)</p> <p>16 oz/gal w/ #33: 3.37 lbs./gal (405 g/l)</p> <p>These are nominal values and may vary slightly with color.</p>
Dry Temp. Resistance	<p>Continuous: 200°F (93°C)</p> <p>Non-Continuous: 250°F (121°C)</p> <p>Discoloration and loss of gloss is observed above 200°F (93°).</p>
Limitations	<ul style="list-style-type: none"> • Epoxies lose gloss, discolor and eventually chalk in sunlight exposure. • Not recommended for immersion service.

Substrates & Surface Preparation

General	Surfaces must be clean and dry. Employ adequate methods to remove dirt, dust, oil and all other contaminants that could interfere with adhesion of the coating.
Steel	<p>For most applications:</p> <p>SSPC-SP6 to obtain a blast profile of 1.0-2.0 mils (25-50 microns). May also be applied over SSPC-SP 3 for certain applications.</p>
Concrete	Concrete must be cured 28 days at 75°F (24°C) and 50% relative humidity or equivalent. Prepare surfaces in accordance with ASTM D4258 Surface Cleaning of Concrete and ASTM D4259 Abrading Concrete. Voids in concrete may require surfacing.

Performance Data

Test Method	System	Results	Report #
ASTM D4541 Adhesion	Blasted Steel 2 ct. 893 SG	1600 psi (Pneumatic)	09453
ASTM D522 Flexibility	Blasted Steel 1 ct. 893 SG	90° bend produced no cracking, ¼" Cylindrical Mandrel Bend	09453

Test reports and additional data available upon written request.

April 2003 replaces June 2002

1000

To the best of our knowledge the technical data contained herein is true and accurate on the date of publication and is subject to change without prior notice. User must contact Carboline Company to verify correctness before specifying or ordering. No guarantee of accuracy is given or implied. We guarantee our products to conform to Carboline quality control. We assume no responsibility for coverage, performance or injuries resulting from use. Liability, if any, is limited to replacement of products. NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY CARBOLINE, EXPRESS OR IMPLIED, STATUTORY, BY OPERATION OF LAW, OR OTHERWISE, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. Carboline® and Carboguard®

Carboguard® 893 SG

Application Equipment

Listed below are general equipment guidelines for the application of this product. Job site conditions may require modifications to these guidelines to achieve the desired results.

General Guidelines:

Spray Application (General) The following spray equipment has been found suitable and is available from manufacturers such as Binks, DeVilbiss and Graco.

Conventional Spray Pressure pot equipped with dual regulators, 3/8" I.D. minimum material hose, .070" I.D. fluid tip and appropriate air cap.

Airless Spray

Pump Ratio:	30:1 (min.)*
GPM Output:	2.5 (min.)
Material Hose:	3/8" I.D. (min.)
Tip Size:	.017"-.021"
Output PSI:	2100-2300
Filter Size:	60 mesh

*Teflon packings are recommended and available from the pump manufacturer.

Brush & Roller (General) Not recommended for tank lining applications except when striping welds. Multiple coats may be required to obtain desired appearance, recommended dry film thickness and adequate hiding. Avoid excessive re-brushing or re-rolling. For best results, tie-in within 10 minutes at 75°F (24°C).

Brush Use a medium bristle brush.

Roller Use 3/8" nap phenolic core roller.

Mixing & Thinning

Mixing Power mix separately, then combine and power mix. DO NOT MIX PARTIAL KITS.

Ratio 1:1 Ratio (A to B)

Thinning Normally not required but may thin as follows:
Spray: Up to 15 oz/gal (12%) with Thinner #10.
Brush & Roller: Up to 16 oz/gal (12%) with Thinner #33.
Use of thinners other than those supplied or recommended by Carboline may adversely affect product performance and void product warranty, whether expressed or implied.

Pot Life 4 Hours at 75°F (24°C)
Pot life ends when coating loses body and begins to sag. Pot life times will be less at higher temperatures.

Cleanup & Safety

Cleanup Use Thinner #2 or Acetone. In case of spillage, absorb and dispose of in accordance with local applicable regulations.

Safety Read and follow all caution statements on this product data sheet and on the MSDS for this product. Employ normal workmanlike safety precautions. Hypersensitive persons should wear protective clothing, gloves and use protective cream on face, hands and all exposed areas.

Ventilation When used in enclosed areas, thorough air circulation must be used during and after application until the coating is cured. The ventilation system should be capable of preventing the solvent vapor concentration from reaching the lower explosion limit for the solvents used. User should test and monitor exposure levels to insure all personnel are below guidelines. If not sure or if not able to monitor levels, use MSHA/NIOSH approved respirator.

Caution This product contains flammable solvents. Keep away from sparks and open flames. All electrical equipment and installations should be made and grounded in accordance with the National Electric Code. In areas where explosion hazards exist, workmen should be required to use non-ferrous tools and wear conductive and non-sparking shoes.

April 2003 replaces June 2002

To the best of our knowledge the technical data contained herein is true and accurate on the date of publication and is subject to change without prior notice. User must contact Carboline Company to verify correctness before specifying or ordering. No guarantee of accuracy is given or implied. We guarantee our products to conform to Carboline quality control. We assume no responsibility for coverage, performance or injuries resulting from use. Liability, if any, is limited to replacement of products. NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY CARBOLINE, EXPRESS OR IMPLIED, BY OPERATION OF LAW, OR OTHERWISE, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. Carboline® and Carboguard® are registered trademarks of Carboline Company.

Application Conditions

Condition	Material	Surface	Ambient	Humidity
Normal	60°-85°F (16°-29°C)	60°-85°F (16°-29°C)	60°-90°F (16°-32°C)	0-80%
Minimum	50°F (10°C)	50°F (10°C)	50°F (10°C)	0%
Maximum	90°F (32°C)	125°F (52°C)	110°F (43°C)	80%

This product simply requires the substrate temperature to be above the dew point. Condensation due to substrate temperatures below the dew point can cause flash rusting on prepared steel and interfere with proper adhesion to the substrate. Special application techniques may be required above or below normal application conditions.

Curing Schedule

Surface Temp. & 50% Relative Humidity	Dry to Recoat Or Topcoat	Maximum Recoat Time
50°F (10°C)	24 Hours	1 Year
60°F (16°C)	10 Hours	1 Year
75°F (24°C)	7 Hours	1 Year
90°F (32°C)	4 Hours	1 Year

These times are based on a 4.0-6.0 mil (100-150 micron) dry film thickness for non-immersion. Higher film thickness, insufficient ventilation or cooler temperatures will require longer cure times and could result in solvent entrapment and premature failure. Excessive humidity or condensation on the surface during curing can interfere with the cure, can cause discoloration and may result in a surface haze. Any haze or blush must be removed by water washing before recoating. If the maximum recoat times have been exceeded, the surface must be abraded by sweep blasting or sanding prior to the application of additional coats. For force curing, contact Carboline Technical Service for specific requirements.

Packaging, Handling & Storage

Shipping Weight (Approximate)	<u>2 Gallon Kit</u> 26 lbs. (12 kg)	<u>10 Gallon Kit</u> 127 lbs. (58 kg)
In White Base (WITE)	<u>1.97 Gallon Kit</u> (Short Filled) Part A	<u>9.84 Gallon Kit</u> (Short Filled) Part A
Flash Point (Setaflash)	Part A: Part B:	75°F (24°C) 75°F (24°C)
Storage (General)	Store Indoors.	
Storage Temperature & Humidity	40° - 110°F (4° - 43°C) 0-100% Relative Humidity	
Shelf Life	Part A & B: Min. 36 months at 75°F (24°C)	
*Shelf Life: (actual stated shelf life) when kept at recommended storage conditions and in original unopened containers.		



350 Hanley Industrial Court, St. Louis, MO 63144-1599
314/644-1000 314/644-4617 (fax) www.carboline.com

An **RPM** Company